

## **PRODUCT INFORMATION**

### **RUSTGUARD – 15:-**

#### **DESCRIPTION:**

- RUSTGUARD – 15 is a water-displacing, solvent cut back, tar based, general purpose, corrosion preventive suitable for the rust proofing and protection of machinery, machinery parts and metals.
- RUSTGUARD – 15 offers a thin black, tough, slightly tacky film capable of being handled and resistant to rubbing when solvent evaporates.
- RUSTGUARD – 15 is suitable for preservation of single components, tools and spares. It is un suitable for internal use in engines and for sub-assemblies employing moving parts or parts with inaccessible recesses

#### **APPLICATION:**

- Rustguard – 15 can be applied by any conventional methods like dipping, brushing or spraying.
- The film must be completely dry before wrapping as it is necessary to protect it from mechanical damage especially at the point of contact with the container.

#### **REMOVAL:**

- RUSTGUARD – 15 can be removed by solvents such as kerosene or mineral spirits. Particular care should be taken to see that small holes such as oil ways are cleaned thoroughly.

#### **SURFACE PREPARATION:**

- The metal surfaces to be protected must be clean, dry and free from rust to achieve the maximum performance of RUSTGUARD – 15.

#### **STORAGE:**

- RUSTGUARD – 15 should be stored at ambient temperatures away from the source of heat and naked flame.

#### **CAUTION:**

- While using RUSTGUARD – 15, ensure adequate ventilation; avoid contact with the skin and DO NOT smoke. The partially cured film should not be exposed to ignition such as flames sparks, excessive heat OR torches.

<b><u>PROPERTIES:</u></b>	<b><u>SPECIFICATIONS:</u></b>
Flash Point , PMCC °C	40
Specific Gravity @ 30 °C , gm/c.c.	0.87
Film Thickness , microns.	50 min.
Non-Volatile matter , weight %	45
Viscosity, Ford Cup, B-4, @ 30 °C; secs.	25
Touch Dry Time ; hrs.	±1
Cure Time; hrs.	±5
Volatile matter , weight %	40
Copper Strip Corrosion 3hrs. @ 100 °C	1.0
Salt Spray Test, 5% NaCl @ 35 °C, 48 hrs	Pass

*The information provided on this page is, to the best of our knowledge accurate, however, it is subject to change without prior notice.*

*We assume no liability for the completeness of it or errors in it.*

**A-406, Kailash Esplanade, L.B.S. Marg, Ghatkopar (West), Mumbai – 400 086.**

**URL: <https://www.hitechpetrochem.com> Mob. Tel.: 9821385015 / 9223385015.**